POWER MAN SONIC.

PG-2V200, 2 Volt 216 AH @ 20-hr. rate PG-2V200 FR 200 AH @ 10-hr. rate


Rechargeable Sealed Lead Acid Battery
Designed for Cyclic, Standby, and Solar Applications






Terminals (mm)

• T11: Threaded insert with 6 mm stud fastener



Physical Dimensions: in (mm)



L: 6.69 (170) W: 4.33 (110) H: 13.78 (350) HT: 12.91 (328)

Tolerances are +/- 0.04 in. (+/- 1mm) and +/- 0.08 in. (+/- 2mm) for height dimensions. All data subject to change without notice.

Features

- Long Service Life Thick plate design and efficient gas recombination yield a service life expectancy of 15 years in standby mode.
- **Low Internal Resistance** Superb high-rate discharge characteristics ensure reliable performance.
- Maintenance-Free, Non-Spillable Proven VRLA technology guarantees safe operation without maintenance and 'nonrestricted article' status for transportation.
- Low Self-Discharge Lead-calcium alloy grids and use of high purity lead account for superior shelf-life characteristics permitting storage for extended periods of time.
- Designed-In Reliability Cutting-edge manufacturing and process control combined with meticulous quality assurance procedures guarantee consistent and dependable performance.

Performance Specifications

Nominal Voltage									
Nominal Capacity									
20-hr. (10.8A to 1.80 volts)									
10-hr. (20.0A to 1.80 volts)									
8-hr. (24.4A to 1.75 volts)									
5-hr. (35.0A to 1.75 volts)									
3-hr. (53.0A to 1.75 volts)									
1-hr. (130.0A to 1.60 volts)									
Approximate Weight 28.0 lbs. (12.71 kg)									
Energy Density (10-hr. rate) 1.07 W-h/in ³ (65.27 W-h/l)									
Specific Energy (10-hr. rate) 14.28 W-h/lb (31.48 W-h/kg)									
Internal Resistance (approx.)									
Shelf Life (% of nominal capacity at 68°F (20°C))									
1 Month									
3 Months									
6 Months									
Operating Temperature Range									
Charge4°F (-20°C) to 122°F (50°C)									
Discharge40°F (-40°C) to 140°F (60°C)									


Case - 2V200 ABS Plastic (UL-94-HB rated)

Case - 2V200 FR ABS Plastic (UL94 V-O flame retardant)



AMPS/WATTS @ 25° C											
FINAL VOLTAGE	30 MIN	45 MIN	1 HR	2 HR	3 HR	4 HR	5 HR	6 HR	8 HR	10 HR	20 HR
	A/W	A/W	A/W	A/W	A/W	A/W	A/W	A/W	A/W	A/W	A/W
1.85	137.2/262.1	104.9/213.1	100.9/208.2	61.4/124.4	47.5/95.1	37.9/76.4	31.8/64.0	28.4/56.8	22.5/45.0	18.8/37.6	10.3/20.6
1.80	159.3/301.3	119.1/238.5	112.6/229.3	67.0/134.6	51.4/102.3	40.8/81.7	34.1/68.3	30.3/60.5	24.0/47.8	20.0/39.8	10.8/21.7
1.75	166.6/312.1	123.5/245.4	117.0/236.6	69.5/138.8	53.0/105.0	42.0/83.8	35.0/69.8	31.0/61.6	24.4/48.5	20.3/40.3	10.9/21.9
1.70	174.3/323.2	128.1/252.2	121.5/243.7	72.0/143.0	54.6/107.7	43.1/85.6	35.9/71.3	31.8/62.9	24.8/49.1	20.5/40.8	11.0/22.1
1.67	179.2/330.3	130.6/255.6	123.9/247.5	73.4/145.3	55.4/109.0	43.8/86.8	36.4/72.2	32.2/63.7	25.0/49.4	20.7/41.1	11.1/22.3
1.60	190.0/345.1	137.0/265.0	130.0/257.0	76.9/150.9	57.9/113.2	45.5/89.6	37.8/75.4	33.3/65.6	25.4/50.2	21.1/41.8	11.4/22.7

Discharge Time vs. Discharge Current



Discharge Current (A)

Charging

Cycle Applications: Limit initial current to less than 20A. Charge until battery voltage (under charge) reaches 2.40 to 2.50 volts at 77°F (25°C) (Temperature Coefficient -5V/C). Hold at 2.40 to 2.50 volts until current drops to under 400mA. Battery is fully charged under these conditions, and charger should be disconnected or switched to "float" voltage.


"Float" or "Stand-By" Service: Hold battery across constant voltage source of 2.25 to 2.30 volts continuously. When held at this voltage, the battery will seek its own current level and maintain itself in a fully charged condition.

Note: Due to the self-discharge characteristics of this type of battery, it is imperative that they be charged within 6 months of storage, otherwise permanent loss of capacity might occur as a result of sulfation.


Further Information

Please refer to our website www.power-sonic.com for a complete range of useful downloads, such as product catalogs, material safety data sheets (MSDS), technical manual, ISO certification, etc..

Discharge Characteristics



Shelf Life & Storage



Contact Information www.power-sonic.com

DOMESTIC SALES
Tel: +1-619-661-2020
Fax: +1-619-661-3650
national-sales@power-sonic.com

CUSTOMER SERVICE
Tel: +1-619-661-2030
Fax: +1-619-661-3648
customer-service@power-sonic.com

TECHNICAL SUPPORT Tel: +1-619-661-2020 Fax: +1-619-661-3648 support@power-sonic.com INTERNATIONAL SALES
Tel: +1-650-364-5001
Fax: +1-650-366-3662
international-sales@power-sonic.com

CORPORATE OFFICE • 7550 Panasonic Way • San Diego, CA 92154 • USA • Tel: +1-619-661-2020 • Fax: +1-619-661-3650